



LOW-DEFECT-DENSITY GAMMA PHASE ALUMINUM OXIDE SUBSTRATES FOR HETEROEPITAXIAL SYNTHESIS

[View U.S. Patent No. 11,879,185 in PDF format.](#)

WARF: P210285US01

Inventors: Chang-Beom Eom, Rui Liu, Paul Evans, Donald Savage, Thomas Kuech

Overview

Oxide thin films have widespread applications in electronic, magnetic, optical materials and devices. Synthesis of oxide thin films via epitaxial growth techniques such as sputtering, molecular beam epitaxy, pulsed laser deposition, and solid phase epitaxy (SPE) largely rely on the single crystal substrates used to provide crystal templates for thin films. Broadening the substrate family for oxides has critical applications in engineering the properties of oxide thin films. The most commonly used substrates for perovskite oxides, for example, SrTiO₃, do not provide substrates with lateral sizes larger than approximately 2 cm, which in some cases limits the technological application of oxide thin films.

The Invention

UW researchers have developed a method for the epitaxial synthesis of thin films of cubic γ -Al₂O₃ with low-defect density. These methods can be employed with large-area α -Al₂O₃ wafers. The synthesis uses SPE to achieve a precise selection of the structural phase of Al₂O₃. The γ -Al₂O₃ thin films produced in this way are candidate substrates for oxide thin films with cubic or hexagonal structures. The use of low defect-density γ -Al₂O₃ layers can broaden the choices of lattice parameters of substrates for oxides and enable large-area processing on low-defect density commercial substrates. SPE in general involves creating an amorphous thin film on a crystalline substrate then heating at a temperature and duration selected to form epitaxial thin films.

Applications

The single crystal γ -Al₂O₃ thin films with low-defect density created via this method can be used as substrates for the synthesis of oxides with cubic or hexagonal structures. The cubic crystallographic symmetry and the value of the lattice parameter are a good match for many oxides, especially the perovskite oxides. Some potential application areas are:

- Piezoelectric PZT thin films for ultrasound and integrated optics applications
- BFO for lead-free piezoelectric applications, KTO for superconductors
- SVO for electrodes for photovoltaic cells and to create smart windows
- Garnets for magneto-optical devices and spintronic devices.
- Highly miscut substrates can also be used to form single domain γ -Al₂O₃, which has potential applications in oxide radiofrequency electronics

Key Benefits

We use cookies on this site to enhance your experience and improve our marketing efforts. By continuing to browse without changing your browser settings to block or delete available α -Al₂O₃ substrates cookies, you agree to the storing of cookies and related technologies on your device. [See our privacy policy.](#) Sessions greater than a

OK



few cm, including integrated optics.

Additional Information

For More Information About the Inventors

- [Paul Evans](#)
- [Chang-Beom Eom](#)
- [Thomas Kuech](#)

Publications

- Liu R, Elleuch O, Wan Z, Zuo P, Janicki TD, Alfieri AD, Babcock SE, Savage DE, Schmidt JR, Evans PG, Kuech TF. Phase Selection and Structure of Low-Defect-Density γ -Al₂O₃ Created by Epitaxial Crystallization of Amorphous Al₂O₃. ACS Appl Mater Interfaces.

Tech Fields

- [Semiconductors & Integrated Circuits : Components & materials](#)

For current licensing status, please contact Michael Carey at mcarey@warf.org or 608-960-9867

We use cookies on this site to enhance your experience and improve our marketing efforts. By continuing to browse without changing your browser settings to block or delete cookies, you agree to the storing of cookies and related technologies on your device. [See our privacy policy.](#)

OK

